

## TECHNICAL DATA SHEET

### USING FIELDS and PROPERTIES

It is a water based printing base used to obtain vivid colors with elastic and soft touching effect.  
It can be printed white and light colored cotton and cotton-polyester blend fabrics.  
Does not dry during the print and block the screen.  
If cured correctly as advised, the dry-wet rubbing and washing fastness are high.  
Rubbing and washing tests should be applied 24 hours after curing.  
Suitable to ecological standards.

### PHYSICAL-CHEMICAL PROPERTIES

**Appearance** : Transparent paste  
**pH** : 4,5-6 (25 °C/ 77 °F)  
**Density** : 1,00 g/ cm<sup>3</sup> (25 °C/ 77 °F)  
**Viscosity** : [(25 °C) sp: 7, rpm: 20 Brookfield ] : 70.000 – 80.000 [mPa.s]

### APPLICATION

**Printing:** In order to have more covering, elasticity, color productivity in white and light colored fabrics double print is advised with flash cure.  
To print on dark colored cotton fabrics, SP 240 – Snow White – WB, GS 603 Fine Mesh Clear White – WB or XP 50 White – WB should be used as underbase.  
To print on polyester fabrics which may cause dye migration, SP 230 Anti Migration – WB should be printed as underbase.

**Screen** : Silk screens that are made of 43 cm/110 inch mesh 70 micron silk – 62 cm/157 inch mesh 55 micron silk.

**Squeegee** : 57 – 62 Shore U type squeegee should be used.

**Mixture** : In need of improving elasticity of XP 50 White-WB, XP 30 Clear Base-WB can be added.  
To color XP 30 Clear Base – WB, OP Series (1-5%) or FR Series (5-15%) pigments can be added.  
To reduce the viscosity SP 209 Regulator – WB (1-3%) can be used.  
Never use water to reduce the viscosity. Before use, please stir the ink well. Do not use any additives that are not advised.  
After using, the screen should be cleaned with the water.

**Curing** : Should be cured at 160 °C/320°F for 1,5 minutes.

### SAFETY and STORAGE

It does not contain harmful substances for inhalation and skin when used. However in case of contact to sensitive organs, such as eyes or mouth wash with plenty of water. If necessary, medical assistance is advised.  
Keep containers dry and tightly closed. Store in a ventilated place between (+5)-(+30) °C/(+41)-(+86)°F of temperature.

It should be consumed within 12 months after the production date.


### PACKING

In 8 kg, 30 kg and 60 kg or 1 gal, 5 gal and 15 gal of plastic packings.



**anadolukimya**  
sanayi ve ticaret ltd. Őti.

Akçaburgaz Mah. 109. Sokak  
No: 8-12 Esenyurt/İSTANBUL  
+90 212 875 77 50 ( 3 lines )  
+90 212 875 08 22  
info@anadolukimya.com  
www.anadolukimya.com

 The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.

---