

Akçaburgaz Mah. 109. Sokak No: 8-12 Esenyurt/ISTANBUL +90 212 875 77 50 (3 lines) +90 212 875 08 22 info@anadolukimya.com www.anadolukimya.com

GS 635 ECOLOGICAL DISCHARGE BASE - WB

TECHNICAL DATA SHEET

PROPERTIES

It is a water based printing base used to obtain excellent discharging with vivid colors and soft touching effect. It can be printed on 100% dischargeable cotton. If cured correctly as advised, the dry-wet rubbing and washing fastness are high.

Rubbing and washing tests should be applied 24 hours after curing.

Suitable to ecological standards.

PROPERTIES

Appearance pН

Transparent paste 6-7,5 (25°C/77°F)

Density

: $1,01 \text{ g/cm}^3 (25 \,^{\circ}\text{C}/77 \,^{\circ}\text{F})$

Viscosity

: [(25 °C) sp: 7, rpm: 20 Brookfield] : 25.000 – 35.000 [mPa.s]

Screen

micron silk should be used.

Squeegee

57 - 62 Shore U type squeegee should be used.

Mixture

To have discharge effect with GS 635 Ecological Discharge Base-WB;

GS 635 Ecological Discharge Base-WB 1000 g FA Series Pigment 10 - 50 g Thiourea Dioxide 60 g

After adding Thiourea Dioxide into GS 635 Ecological Discharge Base, taking into consideration the temperature of the printing room, the prepared discharge base should be

Silk screens that are made of 43 cm/110 inch mesh 70 micron silk - 77 cm/200 inch mesh 48

consumed within 6 hours. Otherwise, the base is damaged and the colours change.

In order to prevent any hairy effect on the surface of the fabric after washing or to achieve a non taking transfoil effect, SP 203 Fixing Agent-WB (2-3 %) can be added into the GS 635

Ecological Discharge Base-WB.

To reduce the viscosity, GS 600 Regulator-WB can be added (1-3 %) into GS 635 Ecological

Discharge Base-WB.

Never use water to reduce the viscosity. Before use, please stir the ink well. Do not use any additives that are not advised. After using, the screen should be cleaned with the water.

Curing

Should be cured at 160 °C/320°F for 2 minutes.

It does not contain harmful substances for inhalation and skin when used. However in case of contact to sensitive organs, such as eyes or mouth wash with plenty of water. If necessary, medical assistance is advised. Keep containers dry and tightly closed. Store in a ventilated place between (+5)-(+30) °C/(+41)-(+86)°F of temperature.

It should be consumed within 12 months after the production date.

In 8 kg and 30 kg or 1 gal and 5 gal of plastic packings.



Akçaburgaz Mah. 109. Sokak No: 8-12 Esenyurt/İSTANBUL +90 212 875 77 50 (3 lines) +90 212 875 08 22 info@anadolukimya.com www.anadolukimya.com



The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.