

Product Information Bulletin

Recommended Parameters



Fabric Types

100% cottor



Mesh

Counts: 86-305 t/in (34-120 t/cm)

Tension: 25-35 n/cm²



Squeegee

Durometer: 60-90, 70/90, 70/90/70

Edge: Sharp

Stroke: Hard flood, Fast stroke *Do not use excess saueeaee pressure.



Non-Phthalate Stencil

Direct: 2 over 2 Capillary/Thick Film: N/A Off Contact: 1/16" (.2cm)



Flash & Cure Temperatures

Flash: 200-210°F (90-100°C) Cure: 320°F (160°C)



Pigment Loading

EQ: N/A MX: N/A PC: N/A

*All percentages listed at % by weight.



Epic Additives

Extender: N/A

Reducer: Curable Reducer- 5% max/ Epic Viscosity Buster-3% max

*All percentages listed at % by weight.



Storage

65-90°F (18-32°C) Avoid direct sunlight. Use within one year of receipt.



Clean Up

Ink degradent or press wash.



Health & Safety

MSDS: www.polyone.com or Contact your local CSR.

11135WHT Epic Olympia Plus White

Wilflex™ Epic Olympia Plus White is an excellent non-phthalate white ink specially formulated for non-bleed 100% Cotton garments. Its fast flash time and superior low after-tack make the ink ideal for use as a flash white. Epic Olympia Plus White has a clean blue undertone for highlight



Highlights

- ▶ High opacity.
- ►Matte finish.
- Excellent fiber mat-down.
- Prints through a wide variety of mesh counts.
- Fast flashing with minimal after-tack. No cooling station required.
- ▶Use as a first-down, underbase flash white or an overprint stand-alone white.
- ▶Odorless.



Printing Tips

- Due to differences in power, height above ink film and efficiency of the flash drying unit, specific dwell time cannot be specified.
- ▶Use consistent, high-tensioned screen mesh to optimize performance properties.
- To increase production speeds, use finer mesh counts for the flash plate to decrease gel time. Set flash dwell times on heated pallets to simulate production. Adjust your settings so that the ink is just dry to the touch.



- ▶Non-phthalate.
- For individual compliance certifications, please visit www.wilflex.com/compliance.



- Perform fusion tests before production. Failure to cure ink properly may result in poor wash fastness, inferior adhesion and unacceptable durability. Ink gel and cure temperatures should be measured using a Thermoprobe placed directly in the wet ink film and verified on the production run substrate(s) and production equipment. It is the responsibility of the printer to determine that the correct ink has been selected for a specific substrate and the application processes meet your customer's standards or specifications.
- Avoid over flashing as it can result in poor inter-coat adhesion of colors.
- Avoid polyester-based fabrics where dye migration will occur.
- ▶ Reducing viscosity will adversely affect opacity.
- Stir plastisols before printing.
- Do not dry clean, bleach or iron printed area.
- Stir plastisols before printing.
- Do not dry clean, bleach or iron printed area.
- ▶NON-CONTAMINATION OF EPIC INKS: Do not add or mix non-Epic inks, additives or extenders with Epic inks. All buckets, palette knives, stirring apparatus, squeegees, flood bars and screens must be cleaned properly and free of phthalates and pvc containing inks. Non-phthalate emulsions and pallet adhesives must be used. Failure to follow these precautions may cause phthalate contamination in violation of consumer protection laws and
- Any application not referred in this product information bulletin should be pre-tested or consultation sought with Wilflex Technical Services Department prior to printing.
- ▶Email: techserviceswilflex@polyone.com